


Accura[®] 48HTR Plastic



Automotive intake manifold used for fit checking and performance testing

A Strong, Rigid & Thermally Resistant SLA[®] Plastic for your most demanding application needs

Applications

- Automotive Testing
 - Under the hood
 - Fluid flow and visualization
 - Intake manifold design analysis and verification
 - Coolant flow analysis
 - Heating Air duct models
 - Transmission fluid flow analysis
- Electronic controls prototypes
- Aerospace wind tunnel models
- High rigidity models
- Long lived prototypes

Features


- Temperature resistant to 130 °C (266 °F)
- High humidity and moisture resistance
- High rigidity
- Low viscosity formulation

Benefits


- Suitable for high temperature testing
- Stable mechanical properties over time
 - Parts maintain modulus in humid environments
 - Extended part life
- Parts are strong and maintain shape
- Fast recoating and cleaning



Impeller design study.



Electronic heat sink prototype.



CPU Cooling fans, and heat sink prototypes.

Technical Data

Liquid Material

Measurement	Condition	Value
Appearance		Clear Amber
Liquid Density	@ 25 °C (77 °F)	1.17 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.23 g/cm ³
Viscosity	@ 30 °C (86 °F)	200 - 250 cps
Penetration Depth (Dp)*		5.5 mils
Critical Exposure (Ec)*		7.4 mJ/cm ²
Tested Build Styles		Viper™ - EXACT™, EXACT™-HR Viper™ Pro - EXACT™

Post-Cured Material

Measurement	Condition	Metric	US
Tensile Strength	ASTM D 638	64 - 67 MPa	9280 - 9720 PSI
Tensile Modulus	ASTM D 638	2800 - 3980 MPa	406 - 577 KSI
Elongation at Break (%)	ASTM D 638	4 - 7%	4 - 7%
Flexural Strength	ASTM D 790	105 - 118 MPa	15200 - 17100 PSI
Flexural Modulus	ASTM D 790	2760 - 3400 MPa	400 - 493 KSI
Impact Strength (Notched Izod)	ASTM D 256	22 - 29 J/m	0.4 - 0.5 ft-lb/in
Heat Deflection Temperature	ASTM D 648		
- UV Postcure Only	@ 66 PSI	65 °C	149 °F
- UV Postcure Only	@ 264 PSI	57 °C	135 °F
- UV + thermal postcure (2 hr @ 160 °C)	@ 66 PSI	130 °C	266 °F
- UV + thermal postcure (2 hr @ 160 °C)	@ 264PSI	110 °C	230 °F
Co-efficient of Thermal Expansion	ASTM E 831-93		
	TMA (T<T _g , < 50 °C)	115 µm/m-°C	64 µin/in-°F
	TMA (T>T _g , > 120 °C)	165 µm/m-°C	92 µin/in-°F
Glass Transition(T _g)	ASTM D 4065-01		
- UV Postcure Only	DMA, E"	62 °C	144 °F
- UV + thermal postcure (2 hr @ 160 °C)	DMA, E"	132 °C	270 °F
Hardness, Shore D	ASTM D 2240	86	86



3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: +1 803.326.4080
Toll-free: +1 800.889.2964
Fax: +1 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product applications, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use. © 2008 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. The 3D logo and Accura[®] are registered trademarks of 3D Systems, Inc.