




Accura[®] 55 plastic

for use with solid-state stereolithography (SLA[®]) systems

Simulate the look and feel of molded ABS with this tough and versatile plastic.



APPLICATIONS

- Automotive interior components
- Short-run production parts
- Electronic components
- Testing of functional assemblies
- Rigid and durable functional prototypes
- Concept and marketing models
- Accurate, durable master patterns for urethane casting

FEATURES

- Durable and rigid material
- Look and feel of molded ABS
- High accuracy with less distortion
- High production speed
- Low viscosity formulation
- Fully developed and tested build styles

BENEFITS

- Produce ABS-like parts without molding or machining
- Increase market opportunities and acceptance for models
- Parts produced within tolerance and faithful to CAD data
- Increase system throughput
- Minimize part cleaning and finishing labor
- Maximize reliability with no user R&D

Accura® 55 plastic

For use with solid-state stereolithography (SLA®) systems

“At Boston Scientific, we test several thousand designs each year. The speed of Accura® 55 has allowed us to produce more models in a shorter time. This greatly increases the number of designs we can test and improves our time to market. In addition, our engineers are amazed that they cannot distinguish the Accura® 55 prototypes from machined ABS and acetal articles.”

– Joseph Cihlar - Rapid Prototyping Team Lead, Boston Scientific

TECHNICAL DATA

Liquid Material

MEASUREMENT	CONDITION	VALUE
Appearance		White
Liquid Density	@ 25 °C (77 °F)	1.13 g/cm ³
Solid Density	@ 25 °C (77 °F)	1.20 g/cm ³
Viscosity	@ 30 °C (86 °F)	155 - 185 cps
Penetration Depth (Dp) *		5.2 mils
Critical Exposure (Ec) *		7.4 mJ/cm ²
Tested Build Styles		EXACT™, FAST™, EXACT-HR

Post-Cured Material

MEASUREMENT	CONDITION	METRIC	US
Tensile Strength	ASTM D 638	63 - 68 MPa	9200 - 9850 PSI
Tensile Modulus	ASTM D 638	3200 MPa - 3380 MPa	460 - 490 KSI
Elongation at Break (%)	ASTM D 638	5 - 8 %	5 - 8 %
Flexural Strength	ASTM D 790	88 - 110 MPa	12830 - 15920 PSI
Flexural Modulus	ASTM D 790	2690 - 3240 MPa	390 - 470 KSI
Impact Strength (Notched Izod)	ASTM D 256	12 - 22 J/m	0.2 - 0.4 ft-lb/in
Impact Resistance (Gardner)	ASTM D5420	1.1 J	0.81 ft-lbs
Heat Deflection Temperature	ASTM D 648 @ 66 PSI @ 264 PSI	55 - 58 °C 51 - 53 °C	131 - 136 °F 123 - 127 °F
Hardness, Shore D		85	85
Co-efficient of Thermal Expansion	ASTM E 831-93 TMA (T<T _g , 0 - 40 °C) TMA (T<T _g , 75 - 140 °C)	61 μm/m-°C 163 μm/m-°C	141 μin/in-°F 326 μin/in-°F
Glass Transition (T _g)	DMA, E''	56 °C	132 °F

* Dp/Ec values are the same on all solid-state laser SLA® systems.



SYSTEMS

TRANSFORM YOUR PRODUCTS

3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: 803.326.4080
Toll-free: 800.889.2964
Fax: 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2007 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. EXACT and FAST are trademarks, and the 3D logo, Accura and SLA are registered trademarks of 3D Systems, Inc.

PN 70717 Issue Date - 09 Mar 07