

DuraForm® PP 100 Plastic



Automotive recliner seat cover made from the tough and rugged DuraForm® PP 100 Plastic.

Applications

- Prototypes where toughness and durability are essential
- Advanced prototypes where actual polypropylene properties are required
- Direct or bridge manufacturing where molded polypropylene properties are desirable

Features

- Polypropylene material
- Tough and rugged
- Excellent chemical resistance
- Good fatigue life and impact resistance
- Optimized for Pro Manufacturing Centers

Benefits

- Test in realistic and challenging environments
- Properties comparable to molded polypropylene
- Properties are consistent and repeatable
- Create living hinges and self-tapping bosses
- Good feature resolution, detail and surface finish
- Build parts up to 900 mm long



Automotive vent grill.



DuraForm® PP100 Plastic can be used for self-tapping screws.

DuraForm® PP 100 Plastic

For use with all Sinterstation® Pro and Sinterstation® HiQ™ series SLS® Systems



DuraForm® PP100 Plastic is strong, flexible and soft to the touch.

Technical Data

General Properties

Measurement	Condition	Metric	U.S.
Density (Sintered Part)	ASTM D792	0.82 - 0.86 g/cm ³	0.82 - 0.86 g/cm ³
Bulk Density (Powder)	ASTM D792	0.46 - 0.47 g/cm ³	0.46 - 0.47 g/cm ³
Tap Density (Powder)	ASTM D792	0.53 - 0.54 g/cm ³	0.53 - 0.54 g/cm ³

Mechanical Properties

Measurement	Condition	Metric	U.S.
Tensile Strength, Ultimate	ASTM D638	20-22 MPa	3.0 - 3.2 ksi
Tensile Strength, Yield	ASTM D638	19-21 MPa	2.8 - 3.1 ksi
Tensile Modulus	ASTM D638	980-1350 MPa	142 - 196 ksi
Elongation at Break	ASTM D638	20-75 %*	20-75 %
Flexural Strength	ASTM D790	30 - 33 MPa	4.4 - 4.8 ksi
Flexural Modulus	ASTM D790	900 - 1150 MPa	130 - 167 ksi
Hardness, Shore D	ASTM D2240	65-68	65-68

* Properties from parts built using 100% virgin powder



3D Systems Corporation
333 Three D Systems Circle
Rock Hill, SC 29730 U.S.A.

Tel: +1 803.326.4080
Toll-free: 800.889.2964
Fax: +1 803.324.8810

moreinfo@3dsystems.com
www.3dsystems.com
NASDAQ: TDSC

Warranty/Disclaimer: The performance characteristics of these products may vary according to product application, operating conditions, material combined with, or with end use. 3D Systems makes no warranties of any type, express or implied, including, but not limited to, the warranties of merchantability or fitness for a particular use.

© 2008 by 3D Systems, Inc. All rights reserved. Specifications subject to change without notice. HiQ™ is a trademark, and the 3D logo, DuraForm®, Sinterstation® and SLS® are registered trademarks of 3D Systems, Inc.